

PRODUCT DATA

7 07 92 00 **Joint Sealants****SONOMERIC® 1****Self-leveling polyurethane sealant for chemical and industrial environments****Description**

Sonomeric® 1 is a ready-to-use self-leveling polyurethane sealant for horizontal joints in chemical and industrial environments. It is weather, chemical, and jet-fuel resistant and has exceptional elongation.

Yield

See page 3 for charts.

Packaging

5 gallon pails (18.93 L); weighing approximately 50 lbs (22.5 kg)

Color

Black

Shelf Life

12 months when properly stored

Storage

Store in unopened containers in a cool, dry area out of direct sunlight. Storing at elevated temperatures will reduce shelf life.

Features

- Weather resistant
- Jet-fuel resistant
- Exceptional elongation
- No mixing
- No priming on most applications

Benefits

- Provides long-term performance
- Withstands chemical attack
- Tolerates joints movement
- Use directly from container
- Easy to apply; speeds jobsite production

Where to Use

APPLICATION

- Airport runways
- Highways and bridges
- Industrial floors
- Driveways and loading docks
- Stadiums

LOCATION

- Horizontal
- Exterior or interior
- Above grade

SUBSTRATE

- Concrete

How to Apply**Joint Preparation**

1. The number of joints and the joint width should be designed for a maximum of $\pm 25\%$ movement.
2. The depth of the sealant should be $1/2$ the width of the joint. The maximum depth is $1/2$ " (13 mm) and the minimum is $1/4$ " (6 mm). Maximum recommended joint width is $1-1/2$ " (38 mm).
3. In deep joints, control the sealant depth by installing Closed-Cell Backer-Rod or Soft Backer-Rod (see Form No. 1026342).
4. Where the joint depth does not permit the use of backer-rod, use a bondbreaker (polyethylene strip) to prevent three-sided adhesion.
5. To maintain the recommended sealant depth, install backer-rod by compressing and rolling it into the joint channel without stretching it lengthwise. Closed-Cell Backer-Rod should be about $1/8$ " (3 mm) larger in diameter than the width of the joint to allow for compression. Soft Backer-Rod should be approximately 25% larger in diameter than the joint width. The sealant does not adhere to it, and no separate bondbreaker is required. Do not prime or puncture the backer-rod.

Technical Data

Composition

Sonomeric® 1 is an asphalt-modified one-component moisture-curing polyurethane

Compliances

- ASTM C 920, Type S, Grade P, Use T, M, Class 25
- Federal Specification TT-S-00230C, Type I, Class A
- Corps of Engineers CRD-C-541, Type I, Class A

Typical Properties

PROPERTY	VALUE
Service temperature range, ° F (° C)	-40 to 180 (-40 to 82)

Test Data

PROPERTY	RESULTS	TEST METHODS
Hardness, Shore A	28	ASTM C 661
100% modulus, psi (MPa)	39 (0.24)	ASTM D 412
Ultimate tensile strength, psi (MPa)	240 (1.7)	ASTM D 412
Ultimate elongation, %	1,200	ASTM D 412
Viscosity, poise	200	Brookfield

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

Surface Preparation

Joint faces must be structurally sound, fully cured, clean, dry, and free of all loose aggregate, paint, oil, grease, wax, mastic compounds, water-proofing compounds, form-release agents, and other contamination.

NEW CONCRETE

Remove all loose material by wire brushing. Sandblast surfaces that have been in contact with form release agents. Fresh concrete must be fully cured at least 28 days. Laitance must be removed by abrading.

OLD CONCRETE PREVIOUSLY CAULKED

Remove all old joint sealing material by mechanical means. If joint sides have absorbed oils, cut away sufficient concrete to ensure clean surface.

Priming

1. Prime steel in contact with Sonomeric® 1 with Primer 733 (see Form No. 1017962) after cleaning to bright metal.
2. Where water immersion may occur, prime joint faces with Primer 733.
3. Apply primer in a thin, uniform film; avoid buildup of excess primer.
4. Allow approximately 15 – 20 minutes drying time before applying sealant.

Application

1. Sonomeric® 1 can be poured from a can or applied by gun.
2. Fill joint from bottom to prevent formation of air voids.
3. Avoid application at extremely low temperatures to prevent moisture condensation and excessive thickening of the sealant.

Clean Up

Immediately after use, wash tools with xylene or Reducer 990.

For Best Performance

- Protect Sonomeric® 1 from traffic until fully cured.
- Do not use on surfaces having a high crown or marked degree of slope.
- Do not paint Sonomeric® 1.
- Do not apply over asphalt dampproofing or asphalt-impregnated joint fillers.
- Do not allow Sonomeric® 1 to come into contact with uncured silicone sealant or with uncured Sonolastic® 150 or 150 Tint Base.
- When subject to periodic water immersion, prime joints with Primer 733 (see Form No. 1017962).
- Do not apply sealant if bed beneath deck or substrate has become saturated with water.
- Do not allow Sonomeric® 1 to come into contact with alcohol-based material or solvents.
- When used on steel, surfaces must be cleaned to bright metal and primed with Primer 733 (see Form No. 1017962).
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

Yield

LINEAR FEET PER GALLON

JOINT DEPTH (INCHES)	JOINT WIDTH (INCHES)						
	1/4	3/8	1/2	5/8	3/4	7/8	1
1/4		308	205	154	122	–	–
3/8		–	–	82	68	58	51
1/2 38		–	–	–	–	51	44

METERS PER LITER

JOINT DEPTH (MM)	JOINT WIDTH (MM)						
	6	10	13	16	19	22	25
6	24.77	16.49	12.39	9.81	–	–	–
10	–	–	–	6.59	5.47	4.66	4.10
13	–	–	–	–	4.10	3.54	3.06

Health and Safety

SONOMERIC® 1

Warning

Sonomeric® 1 contains calcium oxide, talc, light aromatic naphtha, trimethyl benzene, mineral spirits, asphalt, toluene diisocyanate, and silicon dioxide.

Risks

Combustible liquid and vapor. May cause skin and eye irritation. May cause dermatitis and allergic responses. Potential skin and/or respiratory sensitizer. Inhalation of vapors may cause irritation and intoxication with headaches, dizziness and nausea. Ingestion may cause irritation. Reports associate repeated or prolonged occupational overexposure to solvents with permanent brain, nervous system, liver and kidney damage. INTENTIONAL MISUSE BY DELIBERATELY INHALING THE CONTENTS MAY BE HARMFUL OR FATAL.

Precautions

KEEP OUT OF THE REACH OF CHILDREN. KEEP AWAY FROM HEAT, FLAME, AND SOURCES OF IGNITION. Use only with adequate ventilation. Keep container closed. Prevent contact with skin, eyes and clothing. Wash thoroughly after handling. Avoid breathing vapors. Use impervious gloves, goggles and if the TLV is exceeded or if used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable federal, state and local regulations. DO NOT cut or weld on or near empty container. Empty container

may contain explosive vapors or hazardous residues. All label warnings must be observed until container is commercially cleaned or reconditioned.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. SEEK IMMEDIATE MEDICAL ATTENTION. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION. If vomiting occurs, keep the victim's head below hips to avoid aspiration of vomitus into victim's lungs.

Refer to Material Safety Data Sheet (MSDS) for further information.

Proposition 65

This product contains materials listed by the state of California as known to cause cancer, birth defects or other reproductive harm.

VOC Content

1.07 lbs/gal or 128 g/L, less water and exempt solvents.

**For medical emergencies only,
call ChemTrec (1-800-424-9300).**

BASF Building Systems

889 Valley Park Drive
Shakopee, MN, 55379

www.BASFBUILDINGSYSTEMS.COM

Customer Service 800-433-9517

Technical Service 800-243-6739

LIMITED WARRANTY NOTICE: Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

For professional use only. Not for sale to or use by the general public.

Form No. 1019765 7/06
Printed on recycled paper including 10% post-consumer fiber.

© 2006 BASF
Printed in U.S.A.